





Accredited for compliance with ISO/IEC 17025 Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

OIL-WET INCLINING PLATFORM SLIP RESISTANCE TEST

LVT Symphony 4.5mm Vinyl Plank

Prepared for: Australian Select Timbers

Alex Gong

136 Atlas Boulevard

DANDENONG SOUTH VIC 3164

Sample Description: LVT Symphony 4.5mm Vinyl Plank

No. of Specimens &

Size Supplied:

5 off, 229x1000 mm, (Sampling Conducted by Client)

Surface Structure: Smooth

Specimen Preparation: Washed with water and pH neutral detergent, rinsed then dried.

Specimen Configuration: Unfixed

Test Direction: Test conducted parallel with embossed finish.

Joint Type & Width: N/A
Air Temperature: 22°C

Test Standard: AS 4586:2013 Slip resistance classification of new pedestrian surface

materials, Appendix D - Oil Wet Inclining Platform Test

Test Shoe: Leipzig V73-SP

Test Location: ATTAR 44-48 Rocco Drive, Scoresby, VIC, 3179

Test Date: 9 April 2024

Test Personnel: Louie Karkatzoulis and Marcus Bosworth

Displacement Space	Not tested
(rounded to the nearest 0.5cm³/dm²):	Not tested
Displacement Space Assessment Group	Not tested
(Appendix E, AS 4586 - 2013):	13°
Corrected mean overall acceptance angle (α _{ave})	
(rounded down to the nearest degree):	15
Classification:	R10

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked.

Prepared By:

Marcus Bosworth

Compliance and Testing Technician

Reviewed By:

Daniel King BSc/BEng (mat) Hons., MIEAust General Manager - Compliance Services

Approved Signatory





Figure 1: LVT Symphony 4.5mm Vinyl Plank Arrow indicates direction of testing



<u>CLASSIFICATION CRITERIA – AS 4586 - 2013</u> <u>Oil Wet Inclining Platform Test – Appendix D</u>

Compliance

TABLE 5: CLASSIFICATION OF PEDESTRIANSURFACE MATERIALS ACCORDING TO THE OIL-WET INCLINING PLATFORM TEST

Classification	Angle, degrees
No Classification	<6
R9	≥6 <10
R10	≥10 <19
R11	≥19 <27
R12	≥27 <35
R13	≥35